



PMC-780 Dry & PMC-780 Wet

Industrial Liquid Rubber Compounds

PRODUCT OVERVIEW

PMC-780 is a premium performance urethane rubber that offers exceptional strength, durability and abrasion resistance. Mixed two parts A to one part B by weight, PMC-780 pours easily and cures at room temperature with negligible shrinkage to a solid Shore 80A rubber.

Pick The One Best Suited For Your Application: Original **PMC-780 Dry does not exude oil.**

New **PMC-780 Wet contains a built-in release agent** to aid in demolding concrete.

Both are used around the world for casting abrasive materials such as concrete (pre-cast concrete, making concrete stamping pads, etc.) and gypsum plasters with high exotherms. PMC-780 Dry is also commonly used to make rubber mechanical parts of varying configurations (gaskets, wheels, and pullies) as well as ball mill liners and vibration/shock pads.

TECHNICAL OVERVIEW

Key Values: ~**Mixing Ratio:** 2A : 1B by weight or volume ~**Shore A Hardness:** 80
 ~ **Pot Life:** 30 minutes ~**Cure Time/Demold:** Overnight/16 hrs. ~**Color:** Light Amber

Properties	Viscosity	G/CC	Cu. In./Lb.	Tensile Strength	Mix Ratio
Part A	-	-	-	-	200 pbw
Part B	-	-	-	-	100 pbw
Mixed	2,000 cps	1.02	27.2	900 psi	-
Elongation At Break . . .	700%			Die C Tear Strength . . .	200 pli
100% Modulus . . .	400 psi			Shrinkage	negligible

Start By Preparing Your Model -

Some Materials Must Be Sealed . . . To prevent adhesion between the rubber and model surface, models made of porous materials (gypsum plasters, concrete, wood, stone, etc.) must be sealed prior to applying a release agent. *Superseal* (available from Smooth-On) is a fast drying sealer suitable for sealing porous surfaces without interfering with surface detail. A high quality Shellac is suitable for sealing modeling clays that contain sulfur or moisture (water based).

In all cases, the sealing agent should be applied and allowed to completely dry prior to applying a release agent.

Applying A Release Agent . . . A release agent is necessary to facilitate demolding when casting into or over most surfaces. Use a release agent made specifically for mold making (Universal Mold Release available from Smooth-On). A liberal coat of release agent should be applied onto all surfaces that will contact the rubber. **~IMPORTANT:** To ensure thorough coverage, lightly brush the release agent with a soft brush over all surfaces of the model. Follow with a light mist coating and let the release agent dry for 30 minutes.

Because no two applications are quite the same, a small test application to determine suitability for your project is recommended if performance of this material is in question.

Measuring & Mixing . . .

Liquid urethanes are **moisture sensitive** and will absorb atmospheric moisture. Mixing tools and containers should be clean and made of metal, glass or plastic. Materials should be stored and used in a warm environment (72° F / 22° C).

IMPORTANT: Shelf life of product is drastically reduced after opening. Immediately replacing the lids on both containers after dispensing product will prolong the shelf life of the unused product. **XTEND-IT Dry Gas Blanket** (available from Smooth-On) will significantly prolong the shelf life of unused liquid urethane products. These products have a limited shelf life and should be used as soon as possible.

Important: Pre-Mix the Part B before using. After dispensing the required amounts of Parts A and B into mixing container, mix thoroughly for at least 3 minutes making sure that you scrape the sides and bottom of the mixing container several times. **If Mixing Large Quantities** (24 lbs./11 kgs. or more) at one time, we suggest using a mechanical mixer (i.e. Squirrel Mixer or equal) for 3 minutes followed by careful hand mixing for one minute as directed above. Then, pour entire quantity into a new, clean mixing container and do it all over again.

Although this product is formulated to minimize air bubbles in the cured rubber, vacuum degassing will further reduce entrapped air. A pressure casting technique using a pressure chamber can yield totally bubble free castings. Contact Smooth-On or your distributor for further information about vacuum degassing or pressure casting.

Pouring

Curing

Performance

For best results, pour your mixture in a single spot at the lowest point of the containment field. Let the rubber seek its level up and over the model. **A uniform flow will help minimize entrapped air.** The liquid rubber should level off at least 1/2" (1.3 cm) over the highest point of the model surface.

Curing . . . Allow the mold to cure overnight (at least 16 hours) at room temperature (77 F/25 C) before demolding. Cure time can be reduced with mild heat or by adding Smooth-On "Kick-It" Cure Accelerator. Do not cure rubber where temperature is less than 65 F / 18 C.

Post Curing – After rubber has cured at room temperature, heating the rubber to 150° F (65° C) for 4 to 8 hours will increase physical properties and performance.

Using The Mold . . . A release agent should be applied to the mold before each casting. The type of release agent to use depends on the material being cast. The proper release agent for **wax, liquid rubber or thermosetting materials** (Smooth-On liquid plastics) is a spray release made specifically for mold making (Universal Mold Release). Be sure to follow directions for proper application of release agent. Prior to casting **gypsum plasters**, sponge the mold with a soap solution for better plaster flow and easy release. **Especially for releasing concrete**, Smooth-On makes economical water based release concentrate called "IN & OUT".

Performance & Storage - Fully cured rubber is tough, durable and will perform if properly used and stored. The physical life of the rubber depends on how you use it. Contact Smooth-On directly with questions about this material relative to your application.

SAFETY FIRST!

SAFETY FIRST!

SAFETY FIRST!

The Material Safety Data Sheet for this or any Smooth-On product should be read before using and is available upon request. All Smooth-On products are safe to use with proper handling and precautions. Read and follow directions carefully.

Be Careful. **PMC-780** Part A is a TDI prepolymer. Vapors, which can be significant if prepolymer is heated or sprayed, may cause lung damage and sensitization. Use only with adequate ventilation. Contact with skin and eyes may cause severe irritation. Flush eyes with water for 15 minutes and seek immediate medical attention. Remove from skin with soap and water. Prepolymers contain trace amounts of TDI which, if ingested, must be considered a potential carcinogen. Refer to the MSDS for this product. Avoid skin contact by wearing long sleeve garments and latex gloves. If skin contact is made, remove immediately with soap and water. If eye contact is made, flush eyes with water for 15 minutes and seek immediate medical attention.

Important! The information contained in this bulletin is considered accurate. However, no warranty is expressed or implied regarding the accuracy of the data, the results to be obtained from the use thereof, or that any such use will not infringe a patent. User shall determine the suitability of the product for its intended applications and assumes all risk and liability whatsoever in connection therewith.

For Toll-Free Technical Help: (800) 762-0744 • Tel.: (610) 252-5800 • Fax. (610) 252-6200

Website: www.smooth-on.com